



MANUFACTURER NEWLIFE MAGNETICS

MACO MAGNETIC DISPLAY SYETEM SPECIFICATION SHEET

MACO REWRITABLE SERIES


GRW-NS-T012

Edition: A0 NO: NMEQS-MACO 176

FEATURES AND ADVANTAGES:

- White high gloss whiteboard with steel sheeting.
- Compatible with dry erased whiteboard markers, excellent dry-erase ability.
- Steel sheeting is attracted to magnets, easy to apply, remove and change, without residue
- Infinite magnetic receptivity, and rust free.
- Premium PET base, good weather resistance, excellent for durable indoor use.


CONSTRUCTION DRAWING:



STANDARD SIZE:

12milX48"X100'

PACKAGING:



REWRITABLE DATA:

- Rewritable Up To: 20000 times (tested with the whiteboard writing testing machine under ambient temperature and humidity)
- Erase Limitation: For normal whiteboard marker pen, marks can be dry erased off within one month. If the marks are left on a whiteboard for too long and can't be dry erased, please use Whiteboard Cleaner to get them off.

MAGNETIC DATA:

Lifting Weight: ≥ 7.0 (g/cm²)

* Condition: the standard test tool is isotropic rubber magnet 0.7mm (holding strength is about 40g/cm²), test equipment is Tensile Strength Tester.

PHYSICAL DATA:

| | |
|------------------|---------------|
| Total thickness | 300μm (±30) |
| Weight | 670g/M2 (±67) |
| Whiteness | [80, 90] |
| Gloss 60° | [90, 105] |
| Opacity | 100% |
| Water resistance | High |

PROCESS AND STORAGE:

- Working condition: temperature 15°C to 30°C, and relative humidity 30% to 60%.
- Application condition: temperature change is within 40°C daily.
- Storage condition: closed avoiding direct sunlight, in temperature 10°C to 35°C, relative humidity 20% to 70%
- Shelf life: 12 months under storage condition. Unfinished material should be seal-packed.